# Technical data sheet

# **DWH** 745 FL

### Product number #0745

### **Product desciption**

This cold-curing special coating has been developed from the world-renowned "DIAMANT" fine-adjustment and sliding-lining systems, especially for use in highly loaded sliding elements such as slide, support, column, tappet and slide guides, wedge and fitting strips subject to high continuous loads

### **Typical applications**

- dimensionally accurate molding = no machining required
- excellent chemical resistance
- Coefficient of friction approx. <0,05µm (near Teflon®)
- Wear resistance approx. <0,003mm / 100km (similar to hardened steel)
- no stick-slip behavior
- Excellent damping properties improved stiffness for decades in a successful application at well-known machine factories
- Suitable for production, overhaul, repair
- Complete work packages for easy processing
- no special tools or prior knowledge required

### **Characteristics**

- high accuracy
- high load bearing capacity up to 170 N / mm2 (static)
- excellent damping properties
- Complete contact of contact surfaces and thereby good load transfer
- Good adhesion with almost no aging or weathering

### **Chemical resistance**

Please contact our technicians for questions about chemical resistance

### Package sizes

0.5 kg / 1.0 kg / 5.0 kg

DWH 745 FL is delivered in ready-to-use pack sizes. The product consists of two components. Both components must be completely mixed with each other. In order to avoid mixing errors, a portioning of the components into smaller quantities is expressly discouraged.

### **Technical data**

| Technical data                        | Value   |
|---------------------------------------|---|
| Viscosity                             | 12.000 - 15.000   |
| Processing temperatures               | 10°C - 30°C   |
| Pot life at 20°C                      | 45 minutes  |
| Curing time at 20°C                   | 24 hours  |
| moldable at 20°C                      | 12 hours  |
| Specific weight [g/cm³]               | 1,6   |
| Compressive strength dynamic [N/mm²]  | 13 N/mm²  |
| Compressive strength static [N/mm2]   | 130 N/mm²   |
| Thermal permanent stability temporary | -40 up to +80<br>+130   |
| Chemically resistant to               | all chemicals except ketones, esters, aromatics, chlorinated hydrocarbons |

### Storage / shelf life

Store in the original unopened container, dry, cool and frost-free (5  $^{\circ}$  C - + 20  $^{\circ}$  C). life 2 years. Protect from direct sunlight. Higher temperatures reduce the shelf life.

#### **Important instructions**

Please refer to the safety data sheet.





## **Technical data sheet**

### Preparation of the surface

To improve the adhesion, the to be coated guide-surface is provided with a roughening. The roughness should be 0.5 mm (Rt -  $500\mu$ m). The roughening can be made on a milling machine with a knife head with a large feed.

### Mixing process

Add the hardener completely to the resin. Manually mix well with the spatula or with the machine (100 rpm for 2 minutes). Remove the material from the wall and the floor with a spatula and add to the already mixed material.

### Anwendungsbeschreibung

DWH 745 can be:

- poured in a prepared and sealed cavity
- applied and molded on the prepared surface in its pasty form
- injected in a prepared cavity by using a hand-held cartridge

### Venting

### **Putty:**

To avoid air bubbles, the material must be applied thinly on the complete surface.

### Liquid:

Pour the mixture into the cartridge or a limited gap in a long, thin, uninterrupted jet.

### Disposal

Unused residual material from the cans can be disposed of normally (EAKV 170203) when mixed in the correct mixture ratio and completely cured. Unmixed material must be disposed of as chemical waste (EAKV 080111). When the diamond service team is booked, we dispose of the waste.

### **Qualification and Service**

It is recommended that the application be carried out by trained DIAMANT technicians.

In order to guarantee optimum quality and faultfree application, we offer the following services:

- Product Training
- Construction site supervising and on-site work monitoring
- Complete execution of works by our experienced application technicians

Further information can be found in the service data sheet

### **DWH 745 FL #0745**

**DIAMANT Metallplastic GmbH** 

Hontzlarstr. 12 – 14 41238 Mönchengladbach GERMANY

Tel.: +49 (0)2166 – 98360 Fax: +49 (0)2166 – 83025 Mail: info@diamant-polymer.de www.diamant-polymer.de The technical data cited here has been obtained under laboratory conditions and verified on the day of product manufacture through quality assurance processes. This information is subject to change, even without prior notice. The customer is responsible for verifying the current status of the data and should inquire with DIAMANT in this regard prior to ordering the material. Application, use and processing of the product takes place outside of our control and therefore exclusively under the responsibility of the purchaser. However, if a question of liability should arise, it shall be limited - in relation to all damages - to the value of the goods supplied by us and used by you. We guarantee the faultless quality of our products according to the provisions of our general terms and conditions of sales and deliveries. All technical specifications vary depending on loads and application conditions. We are able to issue substantiated application data in individual cases on request.





F047/2017

Date: 07/12/2017